


FIBRANgyps A13 NF



Product Description

Gypsum plasterboard standard type A, CE marked according to UNI EN 520 and NF according to French standard, one decorative ivory face.

Tapered edge BA13, thickness 12,5mm.

No emission of pollutants in the indoor environment – classification A+ in accordance with EN ISO 16000-09.

Applications

Suitable for installation with metal stud of partitions, lining systems and ceilings.

| Features | U. M. | Value | Standard |
|--------------------------------|---------|--|----------|
| Edge | - | BA tapered edge | EN 520 |
| Width | mm | 1200 | EN 520 |
| Thermal conductivity (at 10°C) | W/m K | $\lambda_d = 0,25$ theoretical value | EN 10456 |
| Reaction to fire | Class | A2-s1,d0 | EN 520 |
| Specific Heat Capacity | kJ/kg K | cp = 1,0 theoretical value | EN 10456 |
| Water vapor resistance factor | - | $\mu = 10$ in dry area theoretical value | EN 10456 |

| Type | Thickness [mm] | Weight [kg/m ²] | Length [m] | Long. flex. [N] | Transv. flex [N] |
|------|----------------|-----------------------------|-------------------------|-----------------|------------------|
| BA13 | 12,5 | 9,2 | 2,0-2,5-2,6-2,7-2,8-3,0 | ≥ 600 | ≥ 210 |

Marking on the rear face:

FIBRANgyps A – sp. 12,5mm - NF 39 CE A - EN 520 A2-S1,d0(B) – A+ ; date and time of production- D.o.P number.

FIBRAN reserves the right to alter or amend product specifications without notice. The information included in this publication is correct to the best of our knowledge at the time of printing. Whilst FIBRAN will endeavor to ensure publications are up to date, it is the user's responsibility to check with the company the validity of the information prior to materials' use. For more information visit the web site www.fibran.it.

Date 31/07/2018

FIBRAN S.p.A. via Fiasella 5/11 16121 GENOVA Italy - ph. +39 010 25466.1 fax +39 010 25466.949 - www.fibran.it - tech@fibran.it