

FIBRANgyps JF PLUS



Product Description

Joint filler obtained from a selected mixture of gypsum, aggregates and chemical additives that make the mixture plastic, easy to prepare and with high coverage.

Suitable as first and second coat.

CE Marked 3B according to EN 13963 standard

Applications

Particularly suitable for grouting joints between plasterboards, for grouting fixing screw heads, for repairing small damaged plaster or plasterboard parts. Thanks to its excellent adhesion to the substrate it can also be used as a skim coat.

The setting time of about 4 hours makes it the optimal choice for medium to large construction sites.

Features	U. M.	Value	Standard
Reaction to fire	Class	A1	EN 13501-1
Setting time	min	240*	EN 13963
Performance for joint filling	kg/m ²	0,39	-
Performance for surface finishing	kg/m ²	1,5	-
Preparation	-	Manual and mechanical mixing	-
Rating water/powder	-	1 l / 1,6 kg	-

* indicative times, variable according to weather conditions.

Storage and Application

Store in a cool, dry, ventilated and protected area. Use within 9 months from the date of production. Do not use at temperatures below + 5 ° C and above + 35 ° C.

FIBRAN reserves the right to alter or amend product specifications without notice. The information included in this publication is correct to the best of our knowledge at the time of publishing. Whilst FIBRAN will endeavor to ensure publications are up to date, it is the user's responsibility to check with the company the validity of the information prior to materials' use. For more information visit the web site www.fibran.it.

20/01/2020